

ZL-405

Level ½ Water-Based, Water-Washable Fluorescent Penetrant

ZL-405 is a water-based, water-washable fluorescent penetrant used for finding indications in castings, forgings, extrusions and other materials with rough surfaces commonly found in automotive part applications. ZL-405 is an ideal solution when waste water produced during the inspection process is a concern for the operation. ZL-405 is water based and contains no petroleum distillates which may allow its rinse water to be disposed of directly into the sewage system depending on local regulations.

The penetrant features excellent rinse removability and is self-developing, which means that separate developer may not be necessary depending on the application.

ZL-405 is designed to be environmentally sensitive, meeting EN ISO 3452-2 and can be used in place of any conventional water-washable fluorescent penetrant.



BENEFITS

Reduce environmental footprint and waste-water pollutants

- Reduce water treatment costs and discharge waste process water directly into the sewage system (depending on local regulations) due to minimal water-based contaminants.
- Meet or exceed local discharge regulations with low Biochemical Oxygen Demand (BOD) and Chemical Oxygen Demand (COD) levels.
- Support a healthy environment with water-based penetrants that have minimal occupational health and safety impacts.

Reliably speed up inspection and wash processes

- Identify bright indications with superior sensitivity and low fluorescent background interference.

- Increase throughput and reduce costs by eliminating the developer step of inspection processes depending on procedures and requirements.
- Rapid rinse and post inspection washing of parts thanks to excellent washability properties, due to trade secret chemistry.

FEATURES

- Level ½, very low sensitivity
- Hydrocarbon-free
- Biodegradable
- Excellent water wash removability
- Developer is not required

SPECIFICATION COMPLIANCE

- ISO 3452-2

APPLICATIONS

Defect location: open to surface

Industry types: automotive, general industrial

Ideal applications:

- Castings
- Forgings
- Extrusions
- Rough surfaces
- Ferrous and non-ferrous

Material types:

- Aluminum
- Steel
- Nickel
- Titanium
- Plastic
- Not ideal for magnesium. Testing for compatibility is required.

Additional notes:

- When converting from oil based penetrant it is recommended using a gravity feed if transferring product from a penetrant line
- Automated rinsing may require water pressure adjustments or re-positioning of angles

USE RECOMMENDATIONS

Dry developer	ZP-4B, ZP-4D
Solvent-based developers	SKD-S2, ZP-9F
UV lamps	EV6000, EV6500, ST700
Usage Temperature	40 to 125°F / 5 to 52°C
Storage Temperature	50 to 86°F / 10 to 30°C

PROPERTIES

NDT Method	Fluorescent Penetrant
Type	1
Method(s)	A (W)
Sensitivity Level	½, very low
Required Equipment	UV light source
Flash Point	> 200°F / 100°C
Density	1.011 g/cc / 8.42 lb/gal (1.011 g/ml)
Viscosity (at 100°F/38°C)	4.8 cst (4.8 mm ² /s)
Water Content	79%
Biochemical Oxygen Demand (BOD) (SM 5210 B-2001)	110,000 mg/L
Chemical Oxygen Demand (COD) (SM 5220D-1997)	461,000 mg/l
NPE-Free	Yes

PART NUMBERS & PACKAGING

Packaging	Country of Origin	Part Number
55 gal / 208 L drum	United States	01-3405-45
275 gal / 1,040 L tote		01-3405-67
200 L drum	United Kingdom	056C212
1,000 L tote		056C214

HEALTH AND SAFETY

Review all relevant health and safety information before using this product. For complete health and safety information, refer to the product Safety Data Sheet, which is available at www.magnaflux.com.